

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 06-150929

(43)Date of publication of application : 31.05.1994

(51)Int.Cl.

H01M 4/58
H01M 4/02
H01M 10/40

(21)Application number : 04-302002

(71)Applicant : MATSUSHITA ELECTRIC IND CO
LTD

(22)Date of filing : 12.11.1992


(72)Inventor : OKAMURA KAZUHIRO
NITTA YOSHIAKI
HARAGUCHI KAZUNORI
KOBAYASHI SHIGEO

(54) NON-AQUEOUS ELECTROLYTE SECONDARY BATTERY

(57)Abstract:

PURPOSE: To provide a secondary battery formed by using non-aqueous electrolyte and having an excellent cycle characteristic by using composite oxide made by partially replacing Li in material represented by chemical formula LiNiO_2 with at least one of Na and K, for a positive electrode active material..


CONSTITUTION: In a chemical formula Li_xMyO_2 (wherein M is at least one of Na and K) a positive electrode including active material wherein values of x and y in the formula meet conditions of $0 < x + y \leq 1.0$ and $0 < y \leq 0.3$, a negative electrode using either of lithium, lithium alloy or carbon material into and from which lithium can be inserted and extracted respectively as an active material and non-aqueous material are used to construct a battery. By using such a positive electrode, a non-aqueous electrolyte secondary battery having good cycle time characteristic can be provided.




LEGAL STATUS

[Date of request for examination]	18.11.1997
[Date of sending the examiner's decision of rejection]	
[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]	
[Date of final disposal for application]	
[Patent number]	3049973
[Date of registration]	31.03.2000
[Number of appeal against examiner's decision of rejection]	
[Date of requesting appeal against examiner's decision of rejection]	
[Date of extinction of right]	

【図3】



【図4】



フロントページの続き

(72)発明者 小林 茂雄
大阪府門真市大字門真1006番地 松下電器
産業株式会社内

5

ば正極活物質として化学式 $\text{Li}_x\text{M}_y\text{NiO}_2$ (但し、MはNa, Kの少なくとも1種) において、式中のxおよびyの値が $0 < x + y \leq 1.0$ 、かつ $0 < y \leq 0.3$ の条件を満たすものを用いることにより、サイクル特性に優れた非水電解液二次電池を得ることができる。

【図面の簡単な説明】

【図1】本発明の実施例における円筒形電池の縦断面図

【図2】 $\text{Li}_x\text{M}_y\text{NiO}_2$ (但し、MはNa, Kの少なくとも1種) で、yの値の違いによる初期放電容量の違いを示す図

【図3】 $\text{Li}_x\text{M}_y\text{NiO}_2$ (但し、MはNa, Kの少なくとも1種) で、yの値の違いによる充放電サイクル特


性の違いを示す図

【図4】 $\text{Li}_x\text{M}_{0.1}\text{NiO}_2$ (但し、MはNa, Kの少なくとも1種) で、Mに占めるKとNaの比率の違いによる充放電50サイクル目の放電容量の違いを示す図

【符号の説明】

- 1 電池ケース
- 2 封口板
- 3 絶縁パッキング
- 4 極板群
- 5 正極リード
- 6 負極リード
- 7 絶縁リング

【図1】



【図2】

